

# Micro 200 Vario V7

R2

## QUICK OVERVIEW: STRENGTHS

### The first with variable hygrometry at high grammage

- Vapour control layer with variable hygrometric
- High resistance to tearing and trampling due to heavy grammage
- Easy drying of the bottom side during summer
- Perfect regulation of vapour passage based on temperature and humidity
- Also usable on concrete surfaces



### Composition:

- ① Protective layer in PP
- ② Functional film in PA
- ③ Protective layer in PP

### Codes and measures

Code	Code TOP SK	Width (m)	Length (m)	Pallet (m <sup>2</sup> )
02030148	-	1,5	50	1500

### Features:



### Classification:



### Technical data sheet

Material	PP,PA,PP	
Film	PA	
Colour	Grey	
Mass per unit area	EN 1849-2	200 g/m <sup>2</sup>
Thickness		0,90 mm
Sd value	EN ISO 12572	0,2 - 7 m
Water vapour permeability	EN ISO 12572	~ 100 - 5 g/m <sup>2</sup> /24 h
Water column	EN 20811	>80 cm
Water tightness	EN 13984	passed
Tensile strength MD/CD*	EN 12311-1	400 / 350 N/50mm
Elongation MD/CD*	EN 12311-1	40 / 50 %
Tear resistance MD/CD*	EN 12310-1	250 / 280 N
Fire reaction class	EN 13501-1	E
UV stability		3 months
Temperature resistance		-40°/+80°C

\*MD = longitudinal CD = transversal

Riwega Srl is not responsible for negligent and improper use of its products