


Bituminous vapour barriers


50

R2




DS 28 750 PP TOP SK

Mass per unit area	EN 1849-2	700 g/m ²
Thickness		0,9 mm
Sd value		95 m
TOP SK glue type		bituminous
Tensile strength MD/CD*	EN 12311-1	530 / 350 N/50mm
Tear resistance MD/CD*	EN 12310-1	200 / 200 N
Code TOP SK		02064019




DS 48 1100 PP / DS 48 1100 PP TOP SK

Mass per unit area	EN 1849-2	1100 g/m ²
Thickness		1,1 mm
Sd value		152 m
TOP SK glue type		acrylic
Tensile strength MD/CD*	EN 12311-1	700 / 440 N/50mm
Tear resistance MD/CD*	EN 12310-1	220 / 230 N
Code / Code TOP SK		02064005 / 02064020



DS 48 1300 TOP SK

Mass per unit area	EN 1849-2	1300 g/m ²
Thickness		1,3 mm
Sd value		152 m
TOP SK glue type		acrylic
Tensile strength MD/CD*	EN 12311-1	730 / 450 N/50mm
Tear resistance MD/CD*	EN 12310-1	250 / 250 N
Code TOP SK		02064013



DS 48 2200 TOP SK PP-S

Mass per unit area	EN 1849-2	2200 g/m ²
Thickness		1,8 mm
Sd value		213 m
TOP SK glue type		bituminous
Tensile strength MD/CD*	EN 12311-1	930 / 540 N/50mm
Tear resistance MD/CD*	EN 12310-1	360 / 370 N
Code TOP SK		02064018

*MD = longitudinal CD = transversal

Riweга Srl is not responsible for negligent and improper use of its products