

Micro 90 Vario V7

38
R2

QUICK OVERVIEW: STRENGTHS

The lightest of our variable vapour control layers

- Vapour control layer with variable hygrometric
- Perfect to be used during renovation works on the building envelope
- Variable regulation of vapour passage based on temperature and humidity
- Easy to be laid thanks to its semi-transparency



new
product



Composition:

- ① Functional film in PA
- ② Support layer in PET


Codes and measures

Code	Code TOP SK	Width (m)	Length (m)	Pallet (m ²)
02030147	-	1,5	50	2250

Features:



Classification:



Technical data sheet

Mass per unit area	EN 1849-2	90 g/m ²
Thickness		0,40 mm
Sd value	EN ISO 12572	0,2 - 7 m
Water vapour permeability	EN ISO 12572	~ 100 - 4 g/m ² /24 h
Water column	EN 20811	>200 cm
Water tightness	EN 13984	passed
Tensile strength MD/CD*	EN 12311-1	200 / 190 N/50mm
Elongation MD/CD*	EN 12311-1	25 / 30 %
Tear resistance MD/CD*	EN 12310-1	50 / 40 N
Fire reaction class	EN 13501-1	E
VOC class	ISO 16000	A+
UV stability		3 months
Temperature resistance		-40°/+100°C

*MD = longitudinal CD = transversal

Riwega Srl is not responsible for negligent and improper use of its products