

# DS 1500 Syn Strong

Synthetic vapour and radon barrier

Riwega | eternitycomfort

Technical data sheet



of 23/09/2024

Art. 020640071

Rev. 00

of

-

Material	PP.PE.Alu.PE.PP	 EN 13984
Film	-	
Colour	White	
Roll width	1,5 m	
Roll length	50 m	
Roll weight	15 Kg	
Classification in accordance with UNI 11470 (IT)	A	
Class. in accordance with Önorm B4119/B3661 (AT)	Typ I	
Classification in accordance with SIA 232-1 (CH)	VU-VO G+R	
Conforms to DTU (FR)	31.2	

PROPERTIES	METHOD	UNITS	NOMINAL VALUE
Areal mass	EN 1849-2	g/m <sup>2</sup>	200 (±10g/m <sup>2</sup> )
Air layer equivalent to the vapour passage [Sd]	EN ISO 12572	m	> 1500
Water vapour diffusion [DVA]	EN ISO 12572	g/m <sup>2</sup> / 24h	ca. 0,02
Water column	EN 20811	cm	-
Resistance to water penetration	EN 13984 (EN1928 Met.A)	-	Passed
Tensile strength MD*	EN 12311-1	N/50mm	380 (±30N/50mm)
Tensile strength CD*	EN 12311-1	N/50mm	275 (±30N/50mm)
Elongation MD*	EN 12311-1	%	80 (±20%)
Elongation CD*	EN 12311-1	%	80 (±20%)
Resistance to tearing MD*	EN 12310-1	N	230 (±30N)
Resistance to tearing CD*	EN 12310-1	N	260 (±30N)
Fire reaction	EN 13501-1	Class	E
UV-stability	-	Months	-
Temperature resistance	-	°C	-40 / +100
Radon permeability	ISO 11665-10	m <sup>2</sup> /s	1,64 x 10 <sup>-14</sup>
<b>Durability</b>			
Artificial ageing	EN 1926 (70°C)/EN 1931	-	Passed
Alkali resistance	EN 1847(Typ2)/EN 12311-2	-	Passed

Density	EN 1849-1	Kg/m <sup>3</sup>	308
Thickness	EN 1849-2	mm	0,65 (±0,1)
Vapour resistance coefficient [μ]	EN ISO 12572	-	2307692
Vapour permeability coefficient	-	Kg/m*s*Pa	0,00005*10-12
Thermal conductivity [λ]	-	W/mK	0,22
Specific heat	-	J/KgK	1700

\* MD= Machine Direction; CD= Cross Direction.

Riwega S.r.l. reserves the possibility to review or change these technical values. The updated technical data sheet can be found on the website [www.riwega.com](http://www.riwega.com). This data sheet replaces the previous copy.

